



MARTOXID® PN-6 (12)

Einsatzbeispiele / Applications

Feinteiliges, sehr weiches Aluminiumoxid zur Herstellung von Hochglanzpolituren für Stahl (insbesondere Edelstahl); zur Politur von Nichteisenmetallen, zum Feinschliff von Kunststoffen und Lacken.

Fine-grained, very soft aluminium oxide for the production of high-brilliance polishing agents for mainly stainless steel and steel, as well as for polishing agents for nonferrous metals and for the fine grinding of plastics and lacquers.

Durchschnittsanalyse / Typical analysis

Al ₂ O ₃	[%]	≈ 99.3
Na ₂ O total	[%]	≤ 0.25
CaO	[%]	≈ 0.03
Fe ₂ O ₃	[%]	≈ 0.02
SiO ₂	[%]	≈ 0.01
Glühverlust / Loss on ignition	[%]	≤ 0.2
Spezifische Oberfläche / Specific Surface Area (BET)	[m ² /g]	8 – 15
Primärkorn / Primary Crystal	[µm]	≈ 1
Schüttdichte / Bulk Density	[kg/m ³]	≈ 750

Korngrößenverteilung / Particle Size Distribution (Siebung / Screening)

> 106 µm [%]	0 – 2
106 – 63 µm [%]	1 – 8
63 – 45 µm [%]	5 – 30
< 45 µm [%]	60 – 90

Die oben genannten Werte sind nur als Richtwerte zu verstehen und nicht etwa als zugesicherte Eigenschaften.
The above mentioned values should be taken only as indications and not as guaranteed properties.

Shipping Information

Packaging and minimum order quantity information is available from sales or customer service.

Safety and Handling Information

For specific safety, toxicity and handling information, please refer to the material safety data sheet on this product.

Chemical Registration Numbers

Chem. Bezeichnung / Chem. name: Aluminiumoxid
Formel / formula: Al_2O_3
CAS No.: 1344-28-1
EC/EINECS No.: 215-691-6
UN-Nr.: ---

EUROPE, MIDDLE EAST, AFRICA

Martinswerk GmbH
Kölnener Straße 110
D-50127 Bergheim

Phone: +49-2271-902-0
Fax: +49-2271-902-710

Web: www.martinswerk.de
www.hubermaterials.com

AMERICAS

Huber Engineered Materials
3100 Cumberland Boulevard
Suite 600
Atlanta, Georgia 30339

Phone: +1 (678) 247-7300
Fax: +1 (678) 247-2797

ASIA PACIFIC

Huber Fire Retardant Additives
(Qingdao) Co.Ltd
8th Floor No.2 Building, No.7,
Wuyishan Road, Huangdao District,
Qingdao – China

Phone: +86 532-58792008
Fax: +86 532-58792008

Email: info@martinswerk.com
hubermaterials@huber.com



THERE ARE NO IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Refer to Martinswerk's Standard Conditions of Sale for the only express warranties applicable to the Martinswerk products. Products incorporating Martinswerk products are not warranted by Martinswerk. In no event is Martinswerk liable for consequential damages. **MARTOXID**® is used, applied for, or registered as a trademark of Martinswerk GmbH in various countries around the world.
© July 2017 Martinswerk GmbH