

BORON CARBIDE (B₄C)

Sizing

Boron Carbide is offered according to FEPA F Available micro grit sizes are: F240, F280, F320, F360, F400, F500, F600, F800, F1000, F1200.

Standard macro grit and custom sizes such as: - 200F and -325 F as well as 12, 25 & 45 micron available upon request.

TYPICAL ANALYSIS

B ₄ C	96.17% min.
B ₂ O ₃	0.22%
Total Boron	78.55%
Total Carbon	18.5%
Free Boron	0.24%
Free Carbon	1.27%
Al	0.05%
Fe	0.20% max.
рН	7.0
Magnetic Fe	0.0001% max
Specific Gravity	2.50

TYPICAL APPLICATIONS

Reaction Bonded Parts	Body and Vehicle Armor	Lapping
Hot-Pressed Parts	Nuclear Shielding	Refractory
Sintered Parts	Wear Parts	
Technical Ceramics	Abrasives	



TYPICAL PROPERTIES

- High Hardness
- Abrasion / Wear-Resistance

Abrasives

- Fracture Toughness
- Chemical Inertness
- High Neutron Absorbing Cross Section

www.panadyne.com

Like us on Facebook (f)

Connect with us on LinkedIn in

sales@panadyne.com

Phone 215-444-9315 • Fax 215-444-9317 516 Stump Road • Montgomeryville • Pennsylvania 18936



The information contained in this document is believed to be accurate and reliable but is presented without guarantee or warranty on the part of Panadyne Inc.. Nothing present herein should be interpreted as an authorization or inducement to practice any patented invention without an appropriate license.



BORON CARBIDE TECHNICAL DATA

PROPERTIES	UNITS	VALUE
Physical		
Chemical Formula	-	B ₄ C
Density, ρ	g/cm ³	2.51
Color	-	black or dark gray
Crystal Structure	-	hexagonal
Water Absorption	% @R.T.	ng
Hardness	Mohs	36
Hardness	knoop (kg/mm ²)	ng
Mechanical		
Compressive Strength	MPa @ R.T.	2.9
Tensile Strength	MPa @ R.T.	155
Modulus of Elasticity (Young's Modulus)	GPa	445
Flexural Strength (MOR)	MPa @ R.T.	375
Poisson's Ratio, ບ		0.19
Fracture Toughness, K _{IC}	MPa x m ^{1/2}	ng
Thermal		
Max. Use Temperature (* denotes inert atm.)	°C	2450
Thermal Shock Resistance	ΔT (°C)	ng
Thermal Conductivity	W/m-K @ R.T.	28
Coefficient of Linear Thermal Expansion, α_{I}	μm/m-°C (~25°C through ±1000°C)	5.54
Specific Heat, c _p	cal/g-°C @ R.T.	945
Electrical		
Dielectric Constant	1MHz @ R.T.	ng
Dielectric Strength	kV/mm	ng
Electrical Resistivity	Ωcm @ R.T.	ng

www.panadyne.com

Like us on Facebook

Connect with us on LinkedIn in

sales@panadyne.com

Phone 215-444-9315 • Fax 215-444-9317 516 Stump Road • Montgomeryville • Pennsylvania 18936



is presented without guarantee or warranty on the part of Panadyne Inc.. Nothing present herein should be interpreted as an authorization or inducement to practice any patented invention without an appropriate license.



SINTER GRADE BORON CARBIDE (B₄C)

Sinter Grade Boron Carbide Powders are specially sized to aid in the manufacturing of sintered ceramic parts. They are typically fine powders with an average particle size of less than 10 microns and a specially tailored size distribution.

Contact Panadyne to discuss your sintered B₄C application.



TYPICAL APPLICATIONS

Reaction Bonded Parts

Sintered Parts

Technical Ceramics

Body and Vehicle Armor

Wear Parts

TYPICAL PROPERTIES

- High Hardness
- Abrasion / Wear-Resistance
- Fracture Toughness
- **Chemical Inertness**
- High Neutron Absorbing Cross Section

www.panadyne.com

Like us on Facebook (f)

Connect with us on LinkedIn in

sales@panadyne.com

Phone 215-444-9315 • Fax 215-444-9317 516 Stump Road • Montgomeryville • Pennsylvania 18936



The information contained in this document is believed to be accurate and reliable but is presented without guarantee or warranty on the part of Panadyne Inc.. Nothing present herein should be interpreted as an authorization or inducement to practice any patented invention without an appropriate license.