

BORON CARBIDE (B₄C)

Sizing

Boron Carbide is offered according to FEPA F Available micro grit sizes are: F240, F280, F320, F360, F400, F500, F600, F800, F1000, F1200.

Standard macro grit and custom sizes such as: - 200F and -325 F as well as 12, 25 & 45 micron available upon request.

96.17% min.
0.22%
78.55%
18.5%
0.24%
1.27%
0.05%
0.20% max.
7.0
0.0001% max
2.50

TYPICAL APPLICATIONS			
Reaction Bonded Parts	Body and Vehicle Armor	Lapping	
Hot-Pressed Parts	Nuclear Shielding	Refractory	
Sintered Parts	Wear Parts		
Technical Ceramics	Abrasives		
-			



TYPICAL PROPERTIES
High Hardness
Abrasion / Wear-Resistance
Abrasives
Fracture Toughness
Chemical Inertness
High Neutron Absorbing Cross Section



www.panadyne.com

Like us on Facebook 1



Connect with us on LinkedIn in



sales@panadyne.com





PROPERTIES	UNITS	VALUE
Physical		
Chemical Formula	-	B ₄ C
Density, ρ	g/cm ³	2.51
Color	-	black or dark gray
Crystal Structure	-	hexagonal
Water Absorption	% @R.T.	ng
Hardness	Mohs	36
Hardness	knoop (kg/mm ²)	ng
Mechanical		
Compressive Strength	MPa @ R.T.	2.9
Tensile Strength	MPa @ R.T.	155
Modulus of Elasticity (Young's Modulus)	GPa	445
Flexural Strength (MOR)	MPa @ R.T.	375
Poisson's Ratio, υ		0.19
Fracture Toughness, K _{IC}	MPa x m ^{1/2}	ng
Thermal		
Max. Use Temperature (* denotes inert atm.)	°C	2450
Thermal Shock Resistance	ΔT (°C)	ng
Thermal Conductivity	W/m-K @ R.T.	28
Coefficient of Linear Thermal Expansion, α_{\parallel}	μm/m-°C (~25°C through ±1000°C)	5.54
Specific Heat, c _p	cal/g-°C @ R.T.	945
Electrical		
Dielectric Constant	1MHz @ R.T.	ng
Dielectric Strength	kV/mm	ng
Electrical Resistivity	Ωcm @ R.T.	ng



www.panadyne.com

Like us on Facebook 1



Connect with us on LinkedIn in



sales@panadyne.com

