



MARTOXID[®] TM-4250

Oberflächenbeschichtet / coated

Einsatzbeispiele / Applications

Wärmeleitendes feinstgemahlenes Aluminiumoxid als Füllstoff für Thermoplaste, insbesondere Polyamide. Einsatz für das Thermomanagement und zur Verbesserung der mechanischen, elektrischen, rheologischen Eigenschaften.

Thermally conductive super ground aluminium oxide as a filler in thermoplastics, especially polyamides. Used for thermal management, improvement of mechanical, electrical, and rheological properties.

Durchschnittsanalyse / Typical analysis

Al ₂ O ₃	[%]	> 99.5
Na ₂ O total	[%]	≈ 0.05
CaO	[%]	≈ 0.03
Fe ₂ O ₃	[%]	≈ 0.03
SiO ₂	[%]	≈ 0.08
Spezifische Oberfläche / Specific Surface Area (BET)	[m ² /g]	≈ 3.5
Stampfdichte / Tapped Density	[g/l]	≈ 1200
Korngröße / Particle Size (Cilas 1064)	d ₅₀ [μm]	≈ 1.6
	d ₁₀₀ [μm]	≈ 20

Shipping Information

Transportation classification: not regulated for transportation
Harmonized tariff number: 28182000

Packaging and minimum order quantity information is available from sales or customer service.

Safety and Handling Information

For specific safety, toxicity and handling information, please refer to the material safety data sheet on this product.

Chemical Registration Numbers

Chem. Bezeichnung / Chem. name: Aluminiumoxid
Formel / formula: Al_2O_3
CAS No.: 1344-28-1
EC/EINECS No.: 215-691-6
UN-Nr.: ---

EUROPE, MIDDLE EAST, AFRICA

Martinswerk GmbH
Kölner Straße 110
D-50127 Bergheim

Phone: +49-2271-902-0
Fax: +49-2271-902-710

Web: www.martinswerk.de
www.hubermaterials.com

AMERICAS

Huber Engineered Materials
3100 Cumberland Boulevard
Suite 600
Atlanta, Georgia 30339

Phone: +1 (678) 247-7300
Fax: +1 (678) 247-2797

Email: info@martinswerk.com
hubermaterials@huber.com

ASIA PACIFIC

Huber Engineered Materials
Zhang Ge Zhuang
Huangdao Sub-district
Qingdao, Shangdon
266555 China



THERE ARE NO IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Refer to Martinswerk's Standard Conditions of Sale for the only express warranties applicable to the Martinswerk products. Products incorporating Martinswerk products are not warranted by Martinswerk. In no event is Martinswerk liable for consequential damages. **MARTOXID**® is used, applied for, or registered as a trademark of Martinswerk GmbH in various countries around the world.
© October 2016 Martinswerk GmbH